

L91T19126-3466021502645-Cire à Dorer - NORDIN - Or Classique

COMPOSITION (Matières premières)

Code	Désignation	Poids	Volume	Densité	Prix MP	Prix /Kg
V91T11111	BASE CIRE A DORER	549.820	893.906	0.857	3.370	1.85300
S 5504T	BRONZE OR PALE 7600	45.650	7.951	8.000	29.690	1.35500
S 5505T	BRONZE OR RICHE 7600	179.270	31.223	8.000	23.970	4.29700
S 5503T	E 900 Sombre Gold Bronze	173.610	30.237	8.000	31.250	5.42500
S 5506T	CUIVRE NATUREL 7600	5.330	0.829	8.960	31.120	0.16600
P 4950	NOIR DE FUMEE 101	46.320	35.855	1.800	8.780	0.40700
TOTAUX		1 000.000	1 000.000	1.393		13.50300

C A R A C T E R I S T I Q U E S

				POIDS	VOLUME
Prix /Kg :	13.503	Brillance :		Extrait sec :	45.018
/Li :	18.814	Couvrance :		(Pi+Cha)/Li :	10.609
Densité :	1.393	Viscosité :		Pigment (g/l) :	627.247

CPV :	100.000	CPV / CPVC :	1.734	PdH (cc/100g) :	12.421
--------------	---------	---------------------	-------	------------------------	--------

%	/ TOTAL		/ SEC		ADDITIFS			
	POIDS	VOLUME	POIDS	VOLUME				
Liant	0.000	0.000	0.000	0.000	% Calcium :	0.000	% Zirconium :	0.000
Pigment	45.018	10.609	100.000	100.000	% Plomb :	0.000	% Baryum :	0.000
Charge	0.000	0.000	0.000	0.000	% Cobalt :	0.000	% Lithium :	0.000
Solvant	54.982	89.391			% Manganèse :	0.000	% Métal 1 :	0.000
					% Zinc :	0.000	% Métal 2 :	0.000

% Cendres		% Durcisseur
à 450°C :	45.018	
à 900°C :	45.018	

Etiquetage - Législation européenne			
L1 :	0.000	% Plomb métal :	0.000
L2 :	0.000	% Plomb soluble :	0.000