

L91T19128-L91T19128-Cire à Dorer - Bronze Antique

COMPOSITION (Matières premières)

Code	Désignation	Poids	Volume	Densité	Prix MP	Prix /Kg
V91T11111	BASE CIRE A DORER	650.000	902.760	0.857	3.370	2.19100
P 4950	NOIR DE FUMEE 101	90.000	59.513	1.800	8.780	0.79000
S 5503T	E 900 Sombre Gold Bronze	153.500	22.838	8.000	31.250	4.79700
S 5505T	BRONZE OR RICHE 7600	46.500	6.918	8.000	23.970	1.11500
S 5506T	CUIVRE NATUREL 7600	60.000	7.970	8.960	31.120	1.86700
TOTAUX		1 000.000	1 000.000	1.190		10.76000

CARACTERISTIQUES

				POIDS	VOLUME
Prix /Kg :	10.759	Brillance :		Extrait sec :	35.000
/Li :	12.806	Couvrance :		(Pi+Cha)/Li :	9.724
Densité :	1.190	Viscosité :		Pigment (g/l) :	416.589

CPV :	100.000	CPV / CPVC :	2.266	PdH (cc/100g) :	29.543
--------------	---------	---------------------	-------	------------------------	--------

%	/ TOTAL		/ SEC		ADDITIFS			
	POIDS	VOLUME	POIDS	VOLUME				
Liant	0.000	0.000	0.000	0.000	% Calcium :	0.000	% Zirconium :	0.000
Pigment	35.000	9.724	100.000	100.000	% Plomb :	0.000	% Baryum :	0.000
Charge	0.000	0.000	0.000	0.000	% Cobalt :	0.000	% Lithium :	0.000
Solvant	65.000	90.276			% Manganèse :	0.000	% Métal 1 :	0.000
					% Zinc :	0.000	% Métal 2 :	0.000

% Cendres		% Durcisseur
à 450°C :	35.000	
à 900°C :	35.000	

Etiquetage - Législation européenne			
L1 :	0.000	% Plomb métal :	0.000
L2 :	0.000	% Plomb soluble :	0.000