

L91T19007-L91T19007-Cire à Dorer - Or Pâle

COMPOSITION (Matières premières)

Code	Désignation	Poids	Volume	Densité	Prix MP	Prix /Kg
O 3955T	CEREWAX LS(=MULTIWAX 180M)	109.350	184.054	1.000	9.950	1.08800
O 3954T	CEREXAX L JAUNE (=BARECO ES796)	27.000	45.445	1.000	11.150	0.30100
A 0452	ESSENCE DE TEREBENTHINE	31.500	61.153	0.867	6.140	0.19300
A 0252T	EXXSOL D60	282.150	593.630	0.800	0.925	0.26100
S 5504T	BRONZE OR PALE 7600	550.000	115.717	8.000	23.970	13.18400
TOTAUX		1 000.000	1 000.000	1.683		15.02700

CARACTERISTIQUES

				POIDS	VOLUME
Prix /Kg :	15.027	Brillance :		Extrait sec :	68.635
/Li :	25.293	Couvrance :		(Pi+Cha)/Li :	34.522
Densité :	1.683	Viscosité :		Pigment (g/l) :	925.739

CPV :	100.000	CPV / CPVC :	1.033	PdH (cc/100g) :	1.000
--------------	---------	---------------------	-------	------------------------	-------

%	/ TOTAL		/ SEC		ADDITIFS			
	POIDS	VOLUME	POIDS	VOLUME				
Liant	0.000	0.000	0.000	0.000	% Calcium :	0.000	% Zirconium :	0.000
Pigment	55.000	11.572	80.134	33.520	% Plomb :	0.000	% Baryum :	0.000
Charge	13.635	22.950	19.866	66.480	% Cobalt :	0.000	% Lithium :	0.000
Solvant	31.365	65.478			% Manganèse :	0.000	% Métal 1 :	0.000
					% Zinc :	0.000	% Métal 2 :	0.000

% Cendres		% Durcisseur	Etiquetage - Législation européenne			
à 450°C :	55.000		L1 :	0.000	% Plomb métal :	0.000
à 900°C :	55.000		L2 :	0.000	% Plomb soluble :	0.000