

L91T19122-L91T19122-Cire à Dorer - Antique Clair

COMPOSITION (Matières premières)

Code	Désignation	Poids	Volume	Densité	Prix MP	Prix /Kg
V91T11111	BASE CIRE A DORER	539.500	859.866	0.857	3.370	1.81800
W 8453	PATE 300/53 SERIE NOIRE	50.000	70.046	0.975	6.530	0.32700
S 5503T	E 900 Sombre Gold Bronze	410.500	70.088	8.000	31.250	12.82800
TOTAUX		1 000.000	1 000.000	1.366		14.97300

CARACTERISTIQUES

				POIDS	VOLUME
Prix /Kg :	14.973	Brillance :		Extrait sec :	41.050
/Li :	20.451	Couvrance :		(Pi+Cha)/Li :	7.009
Densité :	1.366	Viscosité :		Pigment (g/l) :	560.703

CPV :	100.000	CPV / CPVC :	1.080	PdH (cc/100g) :	1.000
--------------	---------	---------------------	-------	------------------------	-------

%	/ TOTAL		/ SEC		ADDITIFS			
	POIDS	VOLUME	POIDS	VOLUME				
Liant	0.000	0.000	0.000	0.000	% Calcium :	0.000	% Zirconium :	0.000
Pigment	41.050	7.009	100.000	100.000	% Plomb :	0.000	% Baryum :	0.000
Charge	0.000	0.000	0.000	0.000	% Cobalt :	0.000	% Lithium :	0.000
Solvant	58.950	92.991			% Manganèse :	0.000	% Métal 1 :	0.000
					% Zinc :	0.000	% Métal 2 :	0.000

% Cendres		% Durcisseur	Etiquetage - Législation européenne			
à 450°C :	41.050		L1 :	0.000	% Plomb métal :	0.000
à 900°C :	41.050		L2 :	0.000	% Plomb soluble :	0.000