

L91T19001-L91T19001-Cire à Dorer - Argent

COMPOSITION (Matières premières)

Code	Désignation	Poids	Volume	Densité	Prix MP	Prix /Kg
V91T11111	BASE CIRE A DORER	500.000	735.492	0.857	3.370	1.68500
S 5504T	BRONZE OR PALE 7600	250.000	39.395	8.000	23.970	5.99300
S 5502T	ALUMINIUM STAPA 4	250.000	225.113	1.400	7.740	1.93500
TOTAUX		1 000.000	1 000.000	1.261		9.61300

CARACTERISTIQUES

				POIDS	VOLUME
Prix /Kg :	9.613	Brillance :		Extrait sec :	41.250
/Li :	12.118	Couvrance :		(Pi+Cha)/Li :	17.596
Densité :	1.261	Viscosité :		Pigment (g/l) :	520.011

CPV :	100.000	CPV / CPVC :	1.028	PdH (cc/100g) :	1.000
--------------	---------	---------------------	-------	------------------------	-------

%	/ TOTAL		/ SEC		ADDITIFS			
	POIDS	VOLUME	POIDS	VOLUME				
Liant	0.000	0.000	0.000	0.000	% Calcium :	0.000	% Zirconium :	0.000
Pigment	41.250	17.596	100.000	100.000	% Plomb :	0.000	% Baryum :	0.000
Charge	0.000	0.000	0.000	0.000	% Cobalt :	0.000	% Lithium :	0.000
Solvant	58.750	82.404			% Manganèse :	0.000	% Métal 1 :	0.000
					% Zinc :	0.000	% Métal 2 :	0.000

% Cendres		% Durcisseur	Etiquetage - Législation européenne			
à 450°C :	41.250		L1 :	0.000	% Plomb métal :	0.000
à 900°C :	41.250		L2 :	0.000	% Plomb soluble :	0.000